

Aluminum-Zinc
Alloy (AZ)
Coated
Structural
Quality
Steel
Sheet
for
Steel
Deck

Specification 201M-84
June, 1984

HISTORICAL REFERENCE ONLY
OBSOLETE



CANADIAN
SHEET STEEL
BUILDING INSTITUTE

ALUMINUM-ZINC ALLOY (AZ) COATED STRUCTURAL QUALITY STEEL SHEET FOR STEEL DECK CSSBI SPECIFICATION 201M-84 (Metric Units)

1.0 SCOPE

- 1.1 This specification covers continuously hot-dipped aluminum-zinc alloy (AZ) coated structural quality steel sheet in coils and cut lengths, intended for the manufacture of steel deck. AZ coated steel sheet is not currently recommended for steel deck on which fresh concrete will be placed.

NOTE: In Canada, the product is currently marketed under the tradename Galvalume Steel.

- 1.2 Unless otherwise specified herein, steel sheet supplied to this specification shall meet all applicable requirements of the latest issue of ASTM Standard A792, *General Requirements for Sheet Steel, Aluminum-Zinc Alloy Coated by the Hot-Dip Process*.

NOTE: For zinc coated (galvanized) structural quality steel sheet, refer to CSSBI Specification 101M-84.

2.0 LIMITATIONS

- 2.1 Steel sheet supplied to this specification shall be limited to the following base steel nominal thicknesses: 0.76, 0.91, 1.22 and 1.52 mm. The maximum available width is 1220 mm.
- 2.2 The aluminum-zinc alloy coating on steel sheet supplied to this specification shall be limited to one of the following coating designations: AZ150 or AZ180.

NOTE: AZ150 and AZ180 are metric designations for the aluminum-zinc alloy coating masses currently produced in Canada, expressed in g/m², total both sides of sheet by triple spot test. Coating weight designations listed in ASTM Standard A792 are not applicable.

3.0 BASIS OF PURCHASE

- 3.1 AZ coated steel sheet in coils and cut lengths is produced to decimal thickness and thickness tolerances apply to the base steel nominal thickness, as given in Table 5. Order thickness, given in Table 6, is overall sheet thickness consisting of the base steel nominal thickness and an allowance for the thickness of the coating.
- 3.2 Orders for material to this specification shall include the following information, as necessary, to adequately describe the desired product.
- 3.2.1 State specification designation (CSSBI 201M-84) and grade of material (33 or 37).
- 3.2.2 Specify aluminum-zinc alloy (AZ) coating designation (AZ150 or AZ180).
- 3.2.3 Specify whether chemically treated (passivated) or not chemically treated.
- 3.2.4 Specify whether oiled or not oiled.
- 3.2.5 Specify dimensions; thickness, width and length, if cut lengths.

- 3.2.6 Specify coil-size requirements; maximum mass, acceptable inside diameter (ID), maximum outside diameter (OD).

- 3.2.7 State intended end application.

- 3.2.8 State any special requirements.

NOTE: A typical ordering description is as follows:

"Aluminum-Zinc Alloy (AZ) Coated Structural Quality Steel Sheet, CSSBI 201M-84, Grade 33, Coating Designation AZ150, Chemically Treated, Oiled, 0.80 x 1000 mm by Coil, 10 tonnes maximum, 600 mm ID, for Exposed Roof Deck."

4.0 CHEMICAL REQUIREMENTS

- 4.1 The base steel shall conform to the requirements of chemical composition by cast or heat analysis, as prescribed in Table 1.

TABLE 1 — CHEMICAL REQUIREMENTS, BASE STEEL

	Composition %	
	Grade 33	Grade 37
Carbon, max.	0.20	0.20
Phosphorus, max.	0.04	0.10
Sulphur, max.	0.04	0.04

5.0 MECHANICAL REQUIREMENTS

- 5.1 The base steel shall conform to the mechanical properties prescribed in Table 2 and in 5.2.

TABLE 2 — MECHANICAL REQUIREMENTS, BASE STEEL

	Grade 33	Grade 37
Yield Strength, min.	230 MPa	255 MPa
Tensile Strength, min.	310 MPa	360 MPa
Elongation in 50 mm, min.	20%	18%

- 5.2 The base steel bend test shall be made on coated material. The specimen shall be capable of being bent at room temperature through 180 degrees, longitudinal or transverse, without major cracking of the base steel on the outside of the bent portion (as observed following removal of the coating). The inside diameter of the bend shall be 1.5 times the thickness of the specimen for Grade 33 material and 2.0 times for Grade 37 material.
- 5.3 Two tension tests and two bend tests for base steel shall be made on random samples of finished material from each cast or heat, except that one tension test and one bend test will be sufficient when the finished material from a cast or heat is less than 50 tonnes. When material rolled from one cast or heat differs 1.2 mm or more in thickness, one tension test and one bend test shall be made from both the thickest and thinnest material rolled, regardless of the weight represented. Samples shall be prepared and tested in accordance with the methods specified in ASTM Standard A792, latest issue.

6.0 COATING BEND TEST

- 6.1 Material shall be capable of being bent through

180 degrees in any direction without flaking of the coating on the outside of the bend. Flaking of coating within 6 mm of the edge of the bend specimen shall not be cause for rejection. The radius of the bend shall be as prescribed in Table 3.

6.2 Coating bend test specimens shall be 50 to 100 mm wide. The specimen shall be cut not less than 50 mm from the edges of the test sheet.

TABLE 3 — COATING BEND TEST

Coating Designation	Ratio of Bend Diameter to Thickness of Specimen	
	Grade 33	Grade 37
AZ180	1.5	2.0
AZ150	1.5	2.0

7.0 DIMENSIONS AND TOLERANCES

7.1 Except for flatness tolerances of cut lengths, and thickness tolerances of base steel, all dimensions and tolerances shall be subject to the requirements of ASTM Standard A792, latest issue.

7.2 Flatness tolerances of cut lengths shall not exceed those given in Table 4.

TABLE 4 — FLATNESS TOLERANCES OF CUT LENGTHS

Ordered Thickness, mm	Ordered Width, mm	Flatness Tolerance, mm
To 1.50 incl.	To 900 incl.	12
	Over 900 to 1220 incl.	18
Over 1.50	To 1220 incl.	12

NOTE: Flatness tolerance is defined as the maximum deviation from a horizontal flat surface.

7.3 Thickness tolerances of base steel shall not exceed those given in Table 5.

TABLE 5 — THICKNESS TOLERANCES, BASE STEEL

Base Steel Nominal Thickness, mm	Tolerance on Base Steel Nominal Thickness, Over (+) and Under (-), mm	
	1.52	+.15
1.22	+.15	-.10
0.91	+.10	-.06
0.76	+.10	-.06

NOTE: Thickness is measured on uncoated base steel at any point across the width not less than 10 mm from an edge.

8.0 ORDER THICKNESS

8.1 Order thickness, selected from Table 6, shall be shown on the purchase order.

TABLE 6 — ORDER THICKNESS

Base Steel Nominal Thickness, mm	Order Thickness, mm	
	Aluminum-Zinc Alloy Coating Designation	
	AZ150	AZ180
1.52	1.56	1.57
1.22	1.26	1.27
0.91	0.95	0.96
0.76	0.80	0.81



The Canadian Sheet Steel Building Institute, the national association of the structural sheet steel industry, promotes the use of sheet steel in building construction through engineered design and standards of quality and performance. Activities focus on sheet steel building products and steel building systems for commercial, industrial and institutional applications and similar products and systems for farm applications.

The Institute provides information regarding the standards of design, fabrication and erection, and offers technical assistance in the use of cold formed and pre-engineered steel products. The CSSBI also represents its members in technical matters connected with government, and provides liaison with organizations such as Canadian Standards Association and National Research Council.

CANADIAN SHEET STEEL BUILDING INSTITUTE
305-201 Consumers Road, Willowdale, Ontario M2J 4G8 (416) 493-8780